

90-2007UV Protective UV Tape

Description:

Walco 90-2007UV is a proprietary co-extruded multi-polymer tape featuring UV resistance.

Typical Properties:

Backing:	Multi-Polymer
Adhesive:	Acrylic
Total Tape Thickness:	2.0 mil (0.05mm)
Adhesion to Steel*:	7 oz/in.
Tack Level:	Medium
Tensile Strength:	4500 psi (3.1 MPa)
Elongation:	600%
Performance after UV Exposure:	Clean Removal

Features

- UV resistant film backing and adhesive resists the effects of UV for up to 90 days.
- Removes cleanly after UV exposure.
- Non-staining and non-corrosive adhesive.
- Adheres to metals, plastics & glass surfaces with stable adhesion resulting in good removability during application life.

Application Ideas:

- For aluminum and vinyl windows and frames, window and door glass.
- Garage door panels, metal entry doors and storefronts.
- Painted metal roofing and building panels, aluminum extrusions.

*ADHESION VALUE DETERMINED AS ADHESIVE ONLY

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.