

## 90-3

### Polyethylene Protective Masking

#### Description:

A high-tack protective masking tape for use in interior applications. The product consists of a low density polyethylene self-wound film, coated with a custom formulated water based acrylic adhesive.

#### Typical Properties:

Backing:	Polyethylene
Adhesive:	Acrylic
Nominal Thickness:	5.0 mil
Adhesion Range*:	7-11 oz/in.
Tensile Strength:	MD 3300 psi TD 2700 psi
Elongation:	MD 500% TD 850%

#### Applications

For the automotive glass/mirror application. A non-grazing adhesive with smooth soft release.

Ideal for the masking and protection of metals such as anodized aluminum with a matte or satin finish and matte or textured high pressure laminates.

\*ADHESION VALUE DETERMINED AS ADHESIVE ONLY

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.