

## 90-4005 Polyethylene Protective Tape

### Description:

Walco 90-4005 Polyethylene Protective Tape has a low-tack adhesive system to help provide temporary protection for many metals, plastics and glass materials.

### Typical Properties:

Backing:	Low-Density Polyethylene
Adhesive:	Acrylic
Total Tape Thickness:	4.0 mil (0.10 mm)
Adhesion to Steel*:	5 oz/in.
Tack Level:	Moderate
Tensile Strength:	2500 psi (1.7 MPa)
Elongation:	450%

### Features

- Transparent backing allows visual inspection without tape removal to help save money on reworks.

### Application Ideas:

- Automotive – pre-mask, bumpers, body side molding, paint protection, tail lights or window glass.
- Plastics – molded, acrylic, fiberglass, spas and hot tubs.
- Metals – aluminum: mill finish and stainless, coils or sheets in fabrication, painted flat finish panels.
- General – cultured marble, molded fiberglass or acrylic tubs and spas.

\*ADHESION VALUE DETERMINED AS ADHESIVE ONLY

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.

## 90-4013

### High Tack Polyethylene Protective Tape

#### Description:

Walco 90-4013 has a high-tack adhesive system to help provide temporary protection to a variety of materials that have textured surfaces.

#### Typical Properties:

Backing:	Low-Density Polyethylene
Adhesive:	Acrylic
Total Tape Thickness:	4.0 mil (0.10 mm)
Adhesion to Steel*:	13 oz/in.
Tack Level:	High
Tensile Strength:	2500 psi (1.7 MPa)
Elongation:	450%

#### Features

- Transparent backing allows visual inspection without tape removal to help save money on reworks.

#### Application Ideas:

- Plastics – molded, acrylic, fiberglass, spas and hot tubs, matte high pressure laminates.
- General – cultured marble, woodgrain vinyl laminates, brush and anodized aluminum, matte finished stainless steel.

\*ADHESION VALUE DETERMINED AS ADHESIVE ONLY

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.