

## 10-11

### UHMW-PE / Urethane Foam Composite

**Description:**

One product to solve all your squeak and rattles. Robust urethane backing provides load bearing and gap filling. 5 mil UHMW-PE enhances life of vehicle abrasion resistance. Excellent initial tack and adhesion. High adhesion to low surface energy plastics. Meets OEM fogging specifications. Low fogging qualities. Does not contain any of the 13 chemicals restricted by the Japanese Ministry of Health, Labor and Welfare.

**Typical Properties:**

Foam Density:	25 to 30 lbs./cu.ft.
Hardness (Shore A):	25
Tensile Strength:	80 psi
Elongation:	200%
Recommended Service Temp.:	-40°F to 200°F
Embrittlement Temperature.:	-40°F

**OEM Standards:**

Testing may be required

Chrysler: MS CH612 / MS AY549 <1> (20 lb. Density)

Ford: ESB M3G123 B / WSS M2D496 A5 (20 lb. Density)

GMW: 16879 / 14196 Type 3 & 4 (20 lb. Density)

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.