

## 10-2 Super Soft Vinyl Foam

### Description:

Dynamic cushioning (slow rebound). Highly comfortable for difficult to fix gaps, and flexible for tight radius curves or when irregular surfaces are a critical consideration. Closed cell structure suitable for gasketing or dust, air, and water sealing.

### Typical Properties:

Density:	7 lbs/cu.ft. (112 Kg/m <sup>2</sup> )
Hardness (Shore 00):	14
Force to Compress 25%:	2.0 psi (14 kPa)
Compression Set 30%:	4 (% loss from original height)
Water Absorption:	1.1 (% by volume)
Tensile Strength:	25 psi (173 kPa)
Elongation:	150%
Recommended Service Temp:	-40°F to 180°F (-35°C to -90°C)
Fungi, Oxidation & Water Resistance:	Excellent

### OEM Standards:

Testing may be required

Chrysler: MSAY 500 Type B3

GMW: 15473 Type 2 Class 2

Ford: ESB M3G102 A

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.

## 10-215 Super Soft Vinyl Foam

### Description:

Highly conformable for difficult to fix gaps, and flexible for tight radius curves or when irregular surfaces are a critical consideration. Closed cell structure suitable for gasketing or dust/air/water sealing.

### Typical Properties:

Density	15 lbs./cu. ft.
Hardness(Shore 00)	40
Force to Compress 25%	9 psi
Compression Set 30%	2% (loss from original height)
Water Absorption	1.0% (by volume)
Tensile Strength	80 psi
Elongation	160%
Recommended Service Temp.	-40° F to 180° F
Fungi Resistance	Excellent
Oxidation Resistance	Excellent
Weather Resistance	Excellent

### OEM Standards:

Testing may be required

Chrysler: MSAY500 Type B5

GMW: 15473 Class 2 Type 5

Rev. 1

WALCO MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Typical Properties listed above are not to be construed as specification. User is responsible for determining whether the Walco product is fit for a particular purpose and is suitable for a user's method of application. Walco assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to any product(s). All such advice is given at the buyer's risk, regardless of the legal theory asserted.

Limitation of Remedies and Liability: If the Walco product is proved to be defective, THE EXCLUSIVE REMEDY, AT WALCO'S OPTION, SHALL BE TO REFUND NO MORE THAN THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE WALCO PRODUCT PROVEN TO BE DEFECTIVE. In no event shall Walco be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability. No waiver, alteration, additions or modifications of the foregoing conditions shall be valid unless made in writing and manually signed by an officer of Walco Corporation.